

## Supporting Drill Information to Alacer Gold Announcement

This document provides supporting drill collar locations and composite assay results for the Ardich drilling program referenced in the announcement “Alacer Gold Announces Additional Positive Drill Results for the Çöpler District Including 67.7 Meters at 4.08 grams per tonne Gold Near Surface”, dated February 26, 2018.

Drill collar locations are surveyed in UTM Zone 37N, ED50 grid using differential GPS in units of meters.

Material assay results are listed for drill holes having  $\geq 2.0$  meter downhole length averaging  $\geq 1.00$  g/t gold. Holes containing less than 2.0 meters averaging  $\geq 1.0$  g/t have been excluded.

### Drill Collar Coordinates

Hole ID	Easting	Northing	Elevation	Azimuth	Dip	Depth	Date
AR01	463278.1	4367220	1219.02	85	-50	121	8/11/2017
AR02	463277.9	4367221	1219.1	50	-50	87.8	8/15/2017
AR03	463276.3	4367220	1219.45	265	-70	95.6	8/19/2017
AR04	463335.9	4367196	1214.8	90	-50	171.7	11/14/2017
AR05	463333.9	4367197	1214.71	270	-50	152.2	11/19/2017
AR06	463236	4367264	1214.16	70	-50	227.3	11/30/2017
AR07	463233.5	4367263	1214.2	250	-50	200.2	12/8/2017
AR08	463365.8	4367112	1195.58	40	-50	183.9	12/13/2017
AR09	463365.1	4367110	1195.87	180	-50	134.4	12/24/2017
AR10	463364	4367112	1195.9	315	-60	145.4	1/8/2018
AR11	463282	4367192	1217.54	40	-50	163.7	1/11/2018
AR12	463247.6	4367153	1216.08	40	-60	515.2	1/22/2018
AR13	463249.8	4367249	1215.5	30	-50	168.6	1/21/2018
AR14	463250.4	4367157	1215.58	240	-60	218.4	1/27/2018
AR15	463461.8	4367131	1174.53	50	-60	236	2/3/2018
AR16	463206.8	4367348	1187.27	310	-60	224	2/3/2018
AR17	463463.4	4367129	1175.09	180	-60	182	2/9/2018
AR18	463207.7	4367347	1187.72	50	-60	105.5	2/7/2018

Hole ID	From (m)	To (m)	Interval (m)	Au (g/t)	Oxide/Sulfide	Depth (m)
AR01	39	66	27	0.94	Oxide	121
	72.1	113	40.9	1.43	Oxide	
<b>Including</b>	<b>80</b>	<b>86</b>	<b>6</b>	<b>5.69</b>	<b>Oxide</b>	
AR02	28.7	30.7	2	0.93	Oxide	87.8
	37.7	41.7	4	0.49	Oxide	
	52.7	54.7	2	0.59	Sulfide	
	60.7	63.7	3	0.4	Oxide	
	76.7	87.8	11.1	2.09	Oxide	
AR03	23.3	82.2	58.9	0.87	Oxide	95.6
AR04	13.2	104	90.8	1.79	Oxide	171.7
<b>Including</b>	<b>77.8</b>	<b>99</b>	<b>21.2</b>	<b>5.56</b>	<b>Oxide</b>	
AR05	22.3	25.3	3	0.64	Oxide	152.2
	45.4	79	33.6	0.59	Oxide	
	83	84	1	1.07	Oxide	
	87	109.3	22.3	1.07	Oxide	
	118.8	120.1	1.3	0.62	Oxide	
AR06	44	65	21	0.54	Oxide	227.3
	85	137	52	0.75	Oxide	
	141	146	5	0.44	Oxide	
	198	206	8	1.21	Mixed	
	210	213	3	0.56	Sulfide	
AR07	4	6	2	0.72	Oxide	200.2
	33	39	6	2.16	Oxide	
	63	85.8	22.8	2.53	Oxide	
	103.1	125.6	22.5	3.36	Mixed	
<b>Including</b>	<b>113.4</b>	<b>119.6</b>	<b>6.2</b>	<b>7.6</b>	<b>Oxide</b>	
	131.6	137.6	6	0.92	Sulfide	
AR08	23.1	27.4	4.3	1.57	Oxide	183.9
	31.4	67.8	36.4	1.37	Mixed	
	71.8	77.8	6	0.56	Oxide	
	106	109	3	0.36	Oxide	
AR09	53.3	121	67.7	4.08	Mixed	134.4
<b>Including</b>	<b>92.8</b>	<b>107</b>	<b>14.2</b>	<b>7.21</b>	<b>Oxide</b>	
	<b>115</b>	<b>118</b>	<b>3</b>	<b>18.99</b>	<b>Oxide</b>	
AR10	27	83	56	1.3	Mixed	145.4
<b>Including</b>	<b>54</b>	<b>62</b>	<b>8</b>	<b>3.43</b>	<b>Oxide</b>	

Hole ID	From (m)	To (m)	Interval (m)	Au (g/t)	Oxide/Sulfide	Depth (m)
AR11	46	54	8	0.87	Oxide	163.7
	62	66	4	0.66	Oxide	
	72	101	29	1.89	Oxide	
<b>Including</b>	<b>74</b>	<b>81</b>	<b>7</b>	<b>5.18</b>	<b>Oxide</b>	
	114	116	2	0.9	Oxide	
AR12	58	108	50	2.02	Oxide	515.2
<b>Including</b>	<b>89</b>	<b>102</b>	<b>13</b>	<b>4.38</b>	<b>Oxide</b>	
AR13	33	37	4	0.54	Oxide	168.6
	42	62	20	0.45	Oxide	
	67	109	42	1.04	Oxide	
<b>Including</b>	<b>78</b>	<b>80.3</b>	<b>2.3</b>	<b>7.5</b>	<b>Oxide</b>	
	121.6	124.6	3	0.94	Oxide	
	139.7	158	18.3	0.52	Oxide	
AR14	107.4	135.5	28.1	2.31	Oxide	218.4
<b>Including</b>	<b>117.8</b>	<b>123.8</b>	<b>6</b>	<b>5.6</b>	<b>Sulfide</b>	
AR15	27.6	66.6	39	2.39	Oxide	236
<b>Including</b>	<b>32.6</b>	<b>40.5</b>	<b>7.9</b>	<b>3.87</b>	<b>Oxide</b>	
<b>Including</b>	<b>49.2</b>	<b>51.7</b>	<b>2.5</b>	<b>7.97</b>	<b>Oxide</b>	
<b>Including</b>	<b>58</b>	<b>60</b>	<b>2</b>	<b>6.34</b>	<b>Oxide</b>	
AR16	0	4	4	0.79	Oxide	224
	24	78	54	1.53	Oxide	
<b>Including</b>	<b>45</b>	<b>52</b>	<b>7</b>	<b>5.81</b>	<b>Oxide</b>	
	93	105.4	12.4	0.43	Oxide	
	207.3	210.3	3	1.17	Oxide	
	219	221	2	1.16	Oxide	
AR17	21	58	37	1.67	Sulfide	182
<b>Including</b>	<b>43.5</b>	<b>48.1</b>	<b>4.6</b>	<b>4.81</b>	<b>Sulfide</b>	
	66	71	5	0.9	Oxide	
AR18	0	4	4	1.44	Oxide	105.5
	27.5	47.5	20	1.08	Oxide	
	61.3	63.3	2	0.74	Oxide	
	69.6	76.2	6.6	1.54	Oxide	
<b>Including</b>	<b>70.6</b>	<b>72.4</b>	<b>1.8</b>	<b>3.24</b>	<b>Oxide</b>	