

Supporting Drilling Information to Alacer Gold Announcement

This document provides supporting drill collar locations and composite assay results for the Ardich drilling program referenced in the announcement “Alacer Gold Announces Further Positive Drill Results for the Ardich Gold Project, Including 29.0 Meters at 4.81 Grams Per Tonne”, dated August 26, 2019.

Drill collar locations are surveyed in UTM Zone 37N, ED50 grid using differential GPS in units of meters. All drilling was diamond core drilling with HQ and PQ core sizes. HQ is 63.5mm and PQ is 85mm in diameter.

Drill Collar Coordinates

Hole ID	Easting	Northing	Elevation	Azimuth	Dip	End of Hole (m)
AR101	463845.81	4366976.15	1218.52	220	-70	256.10
AR102	463001.65	4367353.94	1244.12	0	-90	180.00
AR103	463717.79	4366874.91	1222.48	220	-80	210.90
AR104	463001.42	4367356.08	1244.08	0	-60	90.40
AR105	462981.49	4367426.28	1248.92	40	-60	149.50
AR106	463824.58	4366848.39	1239.84	0	-90	248.00
AR107	462949.27	4367341.39	1255.93	270	-60	148.00
AR108	462957.16	4367298.15	1255.41	270	-60	101.00
AR109	463970.61	4366845.76	1249.99	0	-90	160.10
AR110	462886.18	4367198.46	1275.12	270	-60	152.70
AR111	463106.13	4367160.86	1227.79	220	-70	149.50
AR112	463971.64	4366846.20	1250.36	0	-90	50.30
AR113	463107.30	4367162.47	1227.85	40	-70	119.50
AR114	462992.17	4367220.71	1248.12	220	-70	132.60
AR115	463858.76	4366666.41	1296.58	220	-80	230.00
AR116	463174.76	4367080.92	1231.02	220	-70	165.00
AR117	463495.62	4366938.13	1199.26	40	-70	188.00
AR118	463941.23	4366967.63	1228.77	40	-70	277.50
AR119	463489.07	4367002.86	1193.04	40	-60	148.00
AR120	463464.14	4367307.00	1124.61	245	-60	131.00
AR121	463774.86	4366770.04	1254.46	220	-70	191.60
AR122	463765.88	4366965.92	1213.27	320	-60	260.60
AR123	463036.88	4367005.89	1272.40	40	-70	203.00
AR124	463458.71	4367346.05	1121.68	335	-60	131.70
AR125	463971.39	4366844.41	1249.84	40	-70	215.60
AR126	463849.82	4366980.90	1219.28	40	-70	285.00
AR127	463457.69	4367343.55	1121.83	240	-60	86.00
AR128	463035.91	4367006.59	1273.08	220	-70	176.50
AR129	463411.28	4367309.24	1148.61	240	-60	92.00
AR130	463969.77	4366662.25	1294.95	220	-70	213.90
AR131	463397.60	4367345.17	1148.26	280	-60	104.00
AR132	464065.64	4366655.77	1307.67	0	-90	164.60
AR133	463467.70	4366966.62	1203.39	220	-60	186.00
AR134	463400.41	4367345.15	1148.98	45	-60	175.10

Ardich Drill Intercepts

Hole ID	From (m)	To (m)	Interval (m)	Au g/t	Remarks	Depth (m)	Comments	
AR101	192.00	222.60	30.60	1.05	Oxide	256.10	197.50-199.00 Sulfide	
<i>including</i>	218.60	220.60	2.00	7.29	Sulfide			
AR102	0.00	10.00	10.00	0.33	Oxide	180.00	4.00-5.00 Sulfide	
	18.00	49.30	31.30	0.82	Oxide			19.00-20.00 Sulfide
AR103	130.50	159.70	29.20	4.75	Sulfide	210.50	Includes isolated intervals of core loss totaling 0.4m, 130.50-134.50 Oxide	
<i>including</i>	134.50	145.70	11.20	8.09	Sulfide			
<i>including</i>	152.70	158.70	6.00	4.95	Sulfide			
AR104	0.00	8.00	8.00	0.43	Oxide	90.40		
	24.00	59.00	35.00	0.77	Oxide			29.00-30.00 Sulfide
AR105	60.00	69.40	9.40	1.02	Oxide	149.50	60.00-61.00 Sulfide	
	79.40	122.20	42.80	0.70	Oxide			88.00-89.00 and 118.00-119.00 Sulfide
AR106	194.40	199.40	5.00	0.47	Oxide	248.00		
	221.00	227.00	6.00	0.42	Sulfide			
AR107	9.00	33.00	24.00	0.90	Oxide	148.00		
AR108	0.00	36.00	36.00	1.50	Oxide	101.00		
AR109						150.00	Abandoned at 150m and redrilled as AR112	
AR110	3.50	22.00	18.50	1.37	Oxide	152.70	15.00-18.00 Sulfide	
AR111	29.00	60.30	31.30	1.17	Oxide	149.50	31.00-34.00m Sulfide	
	134.30	139.30	5.00	0.49	Mixed			67/33 Oxide-Sulfide
AR112	151.00	185.80	34.80	0.83	Oxide	190.30	173.00-174.00 Sulfide, Includes isolated intervals of core loss totaling 1.0m	
<i>including</i>	151.00	153.00	2.00	3.91	Oxide			
AR113	40.80	47.60	6.80	1.28	Oxide	119.50		
	52.60	74.00	21.40	3.06	Oxide			73.30-74.00 Sulfide
<i>including</i>	66.30	74.00	7.70	5.97	Oxide			73.30-74.00 Sulfide
	86.00	91.00	5.00	0.60	Sulfide			
AR114	13.30	40.00	26.70	2.39	Oxide	132.60	20.60-21.60 Sulfide	
<i>including</i>	22.60	27.60	5.00	5.77	Oxide			
	86.40	95.90	9.50	0.64	Mixed			79/21 Oxide-Sulfide
AR115	158.40	192.00	33.60	0.80	Oxide	230.00	Includes isolated intervals of core loss totaling 1.0m	
	196.00	203.00	7.00	0.66	Oxide			
AR116	82.00	96.20	14.20	2.39	Oxide	165.00		
<i>including</i>	87.00	90.00	3.00	4.42	Oxide			
	120.50	126.50	6.00	1.83	Oxide			123.50-124.50 Sulfide
AR117	131.40	164.50	33.10	4.21	Oxide	188.00	135.10-139.10 Sulfide	
<i>including</i>	133.10	143.70	10.60	10.03	Oxide			135.10-139.10 Sulfide

Hole ID	From (m)	To (m)	Interval (m)	Au g/t	Remarks	Depth (m)	Comments
AR118	164.40	175.50	11.10	1.51	Oxide	277.50	
	180.00	190.00	10.00	0.87	Oxide		
AR119	112.10	126.20	14.10	3.45	Oxide	148.00	Includes isolated intervals of core loss totaling 0.4m. 117.40-118.00 and 119.40-120.40 Sulfide
<i>including</i>	115.40	119.40	4.00	8.09	Oxide		Includes isolated intervals of core loss totaling 0.4m. 117.40-118.00 Sulfide
AR120	8.00	27.60	19.60	2.90	Oxide	131.00	12.50-16.30 Sulfide
<i>including</i>	16.30	19.30	3.00	4.64	Mixed		67/33 Oxide-Sulfide
	47.50	55.50	8.00	0.50	Sulfide		
AR121	158.30	180.60	22.30	0.65	Oxide	191.60	168.50-169.50 Sulfide
AR122	199.20	249.50	50.30	0.97	Sulfide	260.60	205.70-207.70 Oxide
AR123	149.00	165.00	16.00	0.78	Oxide	203.00	162.00-165.00 Sulfide
	196.40	203.00	6.60	0.44	Sulfide		
AR124	36.10	46.70	10.60	1.48	Oxide	131.70	39.10-40.10 and 42.20-43.50 Sulfide
	53.70	92.50	38.80	0.97	Oxide		60.50-61.50, 63.50-64.50 and 72.60-73.70 Sulfide
<i>including</i>	65.50	67.50	2.00	5.15	Oxide		
AR125	177.00	200.50	23.50	1.68	Oxide	215.60	180.00-183.00 Sulfide
<i>including</i>	183.00	186.00	3.00	4.52	Oxide		
AR126	168.60	185.00	16.40	1.24	Oxide	285.00	
AR127	19.10	31.90	12.80	1.95	Oxide	86.00	Includes isolated interval of core loss totaling 0.2m, 21.00-23.10 and 31.30-31.90 Sulfide
AR128	-	-	-	-	-	176.50	No consecutive 5m mineralization (N.S.I.)
AR129	35.80	47.00	11.20	3.02	Oxide	92.00	39.70-40.70 Sulfide
<i>including</i>	41.70	44.70	3.00	9.23	Oxide		
AR130	87.00	90.40	3.40	3.07	Oxide	213.90	
	103.60	116.00	12.40	2.07	Oxide		103.60-105.60 and 106.60-107.60 Sulfide Includes isolated intervals of core loss totaling 0.5m
	131.50	158.80	27.30	0.59	Oxide		
AR131	8.80	13.80	5.00	1.52	Oxide	104.00	
	54.20	58.40	4.20	1.68			
AR132	83.00	97.80	14.80	2.06	Oxide	164.60	
<i>including</i>	84.00	89.00	5.00	4.15	Oxide		
	114.00	122.00	8.00	0.85	Sulfide		
AR133	122.90	173.50	50.60	2.73	Mixed	186.00	62/38 Oxide-Sulfide
<i>including</i>	148.70	159.00	10.30	8.04	Oxide		154.30-155.30 Sulfide

Hole ID	From (m)	To (m)	Interval (m)	Au g/t	Remarks	Depth (m)	Comments
AR134	6.00	11.00	5.00	1.11	Oxide	175.10	
	68.30	105.90	37.60	1.39	Mixed		Includes isolated intervals of core loss totaling 3.0m, 80/20 Oxide-Sulfide
	113.70	142.70	29.00	4.81	Mixed		83/17 Oxide-Sulfide
<i>including</i>	119.70	126.70	7.00	11.74	Mixed		40/60 Oxide-Sulfide

Significant gold intervals reported at a nominal 0.3 g/t gold cut-off and a with a maximum 3.5m contiguous dilution are given in Table 1. All thicknesses are down hole length and true widths are not known at this stage.

Material assay results are listed for drill holes having >5.0 meter downhole length averaging >0.3 g/t gold. Holes containing less than 5.0 meters averaging >0.3 g/t have been excluded. The minimum requirement for higher grade subintervals (including) is >3m length with >1 g/t Au. Intervals with >5g/t Au and less than 3m length have been reported by the corresponding >5g/t Au interval.